

# iRLPD Rutting (AASHTO TP 116)

- Test can be performed on field cores or volumetrics
- Takes only 33 min. to create MSR master curve, which determines resistance of a mixture to rutting at any temperature and under any stress
- Determines allowable traffi

Traffic Category	Traffic Level, MESALs	Critical m*
1	1 to <3	16 to <24
2	3 to <10	10 to <16
3	10 to <30	3 to <10
4	≥ 30	<3

